



## General Properties of Pure Gum†

- Excellent physical properties.
- Excellent abrasion-resistance.
- Excellent low temperature resistance.
- Good resistance to most acids.

† Properties shown based on Rubber Manufacturers Association Sheet Rubber Handbook, second edition.



## SPECIFICATIONS:

### Tan pure gum rubber sheet:

**Style GF40:** 40 Duro hardness (Shore Durometer A)

**Polymer:** Isoprene rubber (natural)

**Common Name:** Natural Rubber Sheet

**ISO/ASTM Designation:** NR

**Talc Free**

Style	ASTM Specification (SI units)	Temp. Range	Durometer	Tensile Strength (psi)	Elongation (%)	Finish
GF40	D 2000 M4AA 421 A13 B13 G21	-40°F to +176°F	35 – 45	3050	600%	Plate

## ORDERING INFORMATION:

Part Number	Gauge x Width (in)	Avg. Length (Linear ft/Roll)	Approx. lbs/Roll
GF40-02x36x67	1/16 x 36	67	65
GF40-04x36x50	1/8 x 36	50	99
GF40-04x36x67	1/8 x 36	67	131
GF40-06x36x50	3/16 x 36	50	149
GF40-06x36x67	3/16 x 36	67	196
GF40-08x36x36	1/4 x 36	36	140
GF40-08x36x50	1/4 x 36	50	199
GF40-12x36x36	3/8 x 36	36	211
GF40-12x36x50	3/8 x 36	50	298
GF40-16x36x18	1/2 x 36	18	140
GF40-24x36x18	3/4 x 36	18	211
GF40-32x36x18	1 x 36	18	281
GF40-02x48x67	1/16 x 48	67	87
GF40-04x48x36	1/8 x 48	36	94
GF40-04x48x50	1/8 x 48	50	131
GF40-06x48x36	3/16 x 48	36	140
GF40-06x48x50	3/16 x 48	50	199
GF40-08x48x18	1/4 x 48	18	94
GF40-08x48x50	1/4 x 48	50	265
GF40-12x48x50	3/8 x 48	50	397
GF40-16x48x25	1/2 x 48	25	264
GF40-24x48x25	3/4 x 48	25	397
GF40-32x48x25	1 x 48	25	530

\* GF40 is being replaced by GF490. See page 14 for specifications. GF40 will still be available as a special order item. Contact KOA for price and minimum.